

DIFFERENT MINERAL ADMIXTURES IN ROLLER COMPACTED CONCRETE

HERSH F. MAHMOOD* and MASOOD ABU-BAKR**

* Civil Engineering Dept., University of Halabja, Kurdistan Region- Iraq

** Civil Engineering Dept., University of Halabja, Kurdistan Region- Iraq

(Accepted for Publication: November 27, 2023)

ABSTRACT

In today's world, all kind of materials are used to improve the materials used in project. Our research is about different mineral admixture on a type of concrete called roller compacted concrete (RCC), which has various uses in paving and dam construction. In this article, the effect of some mineral admixture on the mechanical properties and durability of roller compacted concrete has been investigated. Several mineral admixtures, such as metakaolin, fly ash, silica fume, ground granulated blast furnace slag, rice husk ash, palm oil fuel ash, and, either completely or partially replace cement. In this work, an attempts has been made to find out how adding these mineral admixtures can improve the performance of roller compacted concrete. The strength obtained varies based on the mineral admixtures produced by adding them to roller compacted concrete. The reviewed results of the work done have shown that 5-10% of silica fume, 15-20% of metakaolin, 10-15% of fly Ash, 10% of limestone, 5% of RHA and Coal waste powder, 15% of steel filing, 10% of (Bagasse Ash , natural pozzolan and Basalt rock flour), 15% of GGBS, 10% of POFA and Sugarcane ash, 2% of nano silica cement substitute has the best results on mechanical properties and durability of RCC.

KEYWORDS: GGBS · Fly ash · Metakaolin · Palm oil fuel ash · Silica fume · Rice husk ash, roller compacted concrete (RCC), natural pozzolan (NP).

1. INTRODUCTION

The amount of concrete produced for every human being on Earth is approximately equivalent to one ton of concrete produced worldwide, making concrete the second most used material after water. Environmental issues come from the production of the individual parts of concrete. Since each ton of Portland cement produced results in the emission of one ton of carbon dioxide into the atmosphere, and since cement production makes up about 7% of the total emission of greenhouse gases worldwide, [1].production of cement around 1.6 billion tons of worldwide [2].also Portland cement consumption is increasing significantly in countries that are developing. [3].Roller Compacted Concrete (RCC) was a type of concrete that was invented around 1980[4].Nowadays RCC pavement structures are becoming more common, and there are many places using RCC instead of flexible pavement (asphalt pavement) [5].For many pavement applications, roller-compacted concrete (RCC)

provides a practical, quick-to-build option [6].RCC is made up of the same basic components as conventional concrete, including well-graded aggregates, cementitious materials, and water, but it has a different mixing composition. [7, 8]. RCC has grown in popularity in recent years, especially in the urban areas. Because RCC pavement can be constructed more quickly than conventional concrete pavements and has sufficient structure for truck traffic, it was chosen as a viable solution for developing pavements in this area [9].However, RCC is now being used more often to build pavement because it is more economical. [10].The properties of concrete is increased by the addition of additional components, such as mineral admixtures. [11].Adding more cementitious substances during the concrete manufacturing process can result in significant energy, economic, and environmental pollution advantages. [12].Different mineral admixtures, such as metakaolin, GGBS, fly ash, rice husk ash, palm oil fuel ash, and silica fume, can improve the properties of concrete [13].By adding these

admixtures, the amount of cement decreases, thereby minimizing the impact on the environment. [14].Due to the nature that these admixtures are industrial by-products, disposal problems could also be minimized [15]. According to the mentioned information, the study of the effect of mineral admixture on the properties of RCC is considered valuable

2. PROPERTIES OF MINERAL ADMIXTURE

Physical and chemical properties have been collected from previous studies and are provided in the tables below. Table 1 shows the physical properties of various mineral admixtures, and Table 2 shows the physical properties of different mineral admixtures. Figure 1 depicts the mineral admixtures.

Table (1):- Chemical properties of mineral admixtures

	Metakaolin [16]	Fly Ash [17]	Silica fume [18]	GGBS [19]	RHA [20]	POFA (Palm-oil-fuel-ash) [21]
SiO ₂	80.76	34.5	91.6	37	62.96	50.3
Al ₂ O ₃	15.69	12.8	1.69	13	22.73	4.74
Fe ₂ O ₃	0.04	23.6	1.68	0.6	0.21	8.08
CaO	1.46	19	0.91	40	0.26	5.19
MgO	0.05	2.27	---	8	0.01	3.22
K ₂ O	0.04	2.08	1.19	0.6	0.45	11.8
Na ₂ O	0.01	---	---	0.3	---	0.1
MnO	--	---	---	---	---	--

Table (2):- physical properties of mineral admixtures

Physical properties	Metakaolin [16]	Fly Ash [22]	Silica fume [23]	GGBS [23]	RHA [24]	POFA (Palm-oil-fuel-ash)[25]
specific gravity	2.7	2.645	2.24	2.9	2.23	2.15
Specific surface (cm ² /g)	----	6500	19995	4180	5980	1710



Fly Ash



Silica Fume



GGBS



metakaolin



POFA



Sugarcane Ash

Fig.(1):-depicts the mineral admixtures. . [53], [35], [50], [35], [52], [53]

3. The Evaluation of the Effect of Mineral Admixtures on The Compressive Strength of RCC was Done in The Article.

Compressive strength is the most basic qualitative measure of a concrete's mechanical properties, and it is often employed by design standards and regulations to determine whether a concrete mixture is suitable for a certain application. Because RCC has a compressive strength comparable to that of conventional concrete, the use of different types of minerals admixture has an effect on the RCC's compressive strength. In the study we have done, we want to show what percentage of mineral admixture showed the best increase compressive strength. In one of the experiment replacing cement with metakaolin compressive strength increase due to the metakaolin addition, with a maximum value of 53.1% related to 20% cement replacement for RCC tested at 7 days, and a maximum value of 41.8% related with 15% MK. At 90 days of age. [16].

These results show that metakaolin is a good substitute for cement and helps in filling the void in the mixture and increase the life of RCC due to slow hydration. Through specimen testing, RCC mixes with high strengths were developed. It is obvious that the addition of fly ash and pozzolan can provide excellent RCC strength, especially over a long period of time. Approximately 20% replacement is suitable for produce long-term compressive strength and reduced accumulative heat of hydration. [28].

According to this result, the effect of fly ash can be considered close to metakaolin. The compressive strength of RCC was increased by 33.6 MPa and 30.6 MPa, respectively, when 10% of the cement was replaced with Silica Fume and Fly ash at 28 days. And when mixed both together with the dosages (7.5%) the optimal compressive strength of roller compacting concrete is increased by 34.2 MPa. [31].

Silica fume and slag were utilized the compressive strength enhancement was about 13.9% with the optimum dosages (5, 27.5) respectively. [29]. The optimal amount of nano silica is up to 2%, and it has been observed that adding more nano silica than 2% causes a gradual decrease in the compressive strength of RCC. [30].

Silica fumes have been used in combination with other materials and this shows that the combination of different mineral admixture can

improve the properties of concrete. GGBS improved the mechanical properties of RCC concrete. GGBS enhanced adhesion and filled in the voids of pores and cracks. Furthermore, it prevented crack propagation. [32]. In the research the results was found that the average strengths of all concrete specimens at 28 and 56 days were improved by 38% and 51%, respectively, compared to that of the 7 days, and an important strength development was noticed when the curing age was increased. This can be explained by the fact that the GGBS had a higher hydration rate at later curing ages, which led to the creation of secondary C-S-H gel and a denser microstructure in the cementitious matrix. [19].

Due of the finer and greater specific surface area of RHA particles compared to cement, the optimum w/c ratio rises as the replacement ratio of RHA increases. In comparison to the control samples, compressive strength is improved when RHA is used to replace cement in the range of 5 to 15%. It is because of the amorphous silica in RHA that when it comes into contact with cement, it reacts and creates C-H-S. The main cause of the strength in pozzolanic samples is C-H-S. The compressive strength decreases when the RHA is added outside of the previously specified range, certainly as a result of an increase in the optimum w/c ratio for a constant cementation material content that reduces compaction effort. [26]. RHA enhances the mechanical properties of concrete, reduces permeability properties, and greatly increases its durability because of its high activity and high specific surface area. [27].

According to the results mentioned above, it can be said that due to the fineness of the mineral admixture that replaces cement, the void of mixtures is filled, and it improves their Density and strength. In RCC, due to low water cement ratio (W/C), hydration takes place slowly and this helps the age of RCC.

However, due to their slow hydration of mineral admixture during the mix, the long-term strength and age of RCC increases. It may be seen in future experiments that by using mineral admixture and increased W/C a smoother surface can be reached, which is a big challenge in the RCC pavements. We tried to summarize the optimum of each mineral admixture and its effect. According to the Data in table 3 and mentioned above, the type of optimal mineral admixture in roller concrete can be written as (FA, MK, GGBS, SF, RHA, N.P, steel filling,

POFA, sugarcane ash, basalt flour, CWP).

4. The evaluation of the effect of mineral admixtures on the durability of RCC was done in the article.

The durability of concrete materials is critical when analyzing the life cycle of constructions. In general, concrete durability is primarily concerned with resistance to characteristics such as sulphate, chloride, and acid corrosion solution. However, just a few investigations on ammonium nitrate solution have been done. As mentioned above that RHA improved compressive strength, also enhancing durability of the RCC concrete with a better result. The reasons are that RHA reduces $\text{Ca}(\text{OH})_2$ and clearly improves the pore structure, providing a denser micro-structure, decreased penetrability, and hence improved durability. Several studies have shown that RHA significantly improves the durability of concrete. RHA with different replacement amounts ranging from 5% and 20% have improved the durability of RCC. [44, 45, 46, 47]. When GGBS is replaced in cement, the load carrying capacity and compressive potency of concrete are increased to their maximum. However compressive strength decreases in acid attack as GGBS content increases. But the Corrosion resistance of fiber content increases with high amount of replacement of GGBS. [23, 32, 49, 50, 51, 52].

In terms of durability, Metkaolin had been shown to lower water permeability, absorption, and chloride permeability as the replacement percentage increased. This may be due to the filler effect of Metkaolin particles significantly reducing the concrete's permeability or porosity. [16, 36, 37]. As the amount of silica fume in RCC concrete increased it also increased the resistance to chloride ion penetration. Also by using it there was a reduction in water-binder ratio this makes Concrete's ability to absorb water was significantly lowered. The ratio of (5-

25) % may also enhanced the mechanical and durability properties of RCC. [31, 33, 34, 35, 36].

The permeability of RCC with fly ash was low after 28 days of curing, but as the age developed, it became more impermeable and achieved significant imperviousness. This is because the pozzolanic reaction is low at the beginning. The ratio of replacement of fly ash ranges (5-15) % to improve both mechanical and durability properties of RCC concrete. [22, 31, 35, 39, 40].

Oil Fuel Ash (POFA), is a byproduct of biomass energy waste used to substitute cement. POFA enhances the pozzolanic reaction by generating more calcium silicate hydrates. Under ammonium nitrate solution, POFA improves the deterioration of RCC concrete and this improve the durability with arranges around (10%) of cement replacement.

According to results above, with increasing density and decreasing voids in RCC, water permeability of RCC reduced and RCC can have longer life. Penetration of water and any liquid into the concrete in different season leads to concrete failure and reduced durability of concrete. Therefore, as in the previous section, we mention the order of optimal mineral admixture that have a better role in improve the durability of RCC. The reviewed results of the work done have shown that optimum type respectively RHA, fly Ash, GGBS, metakaolin, silica fume, Coal waste powder, 10% of (Bagasse Ash, natural pozzolan and Basalt rock flour),, 10% of limestone, 15% of steel filing, , 10% of POFA and Sugarcane ash, 2% of nano silica cement substitute has the best results on durability of RCC.

4. Summary of the all mineral admixtures

All of the mineral admixtures of the optimal amount of cement replacement with desired conclusions/remarks and the type of concrete used for the research are given in Table3.

Table (3):-Mineral admixture used in past

Mineral admixture	author	year	% replacement	Conclusion
Silica fume	(A. Ashteyat et al) [32].	2022	5%	increase compressive strength, increase tensile strength, decreasing the water absorption
	(Ch.Chennakesava)[33].	2014	5%	increase in flexural strength of about 5.6%
	(M. Adamu et al)[34]	2017	5%	Reduction in compressive strength was higher for fly ash mineral filler than silica fume which was mainly due to the slower pozzolanic reaction of fly ash. Replacing fly ash with silica as a mineral filler was successful in mitigating loss in compressive strength for up to 20%CR.
	(C. Xupeng et al)[35]	2021	25%	increase 30% of compressive strength and 15% of tensile strength
	(A. Kumar et al)[30]	2021	10%	The compressive strength of mixtures increases by 15% and The tensile strength of mixtures increases by 9%, The water absorption of roller compacted concrete was recorded as 1%.
Metakaolin	(A. A. Hamzah et all)[36]	2008	20%	metakaolin increase in compressive strength of about 5% , increase flexural strength, increase tensile strength
	(C.Xupeng et all)[35]	2021	50%	Increase 30% of compressive strength and 15% of tensile strength.
	(M. Abu-Bakr at al.)[15]	2022	20%	Increase in compressive strength of about 53%, increase in tensile strength of about 20%, increase freezing and thawing resistance and permeability decreases.
FLY Ash	(S. I. Sarsam) [21]	2021	20-30-40%	The flexural strength of dense graded mixtures increases by 63% at 20 % replacement by fly ash while it declines by at (30 and 40) %replacement.
	(M. Adamu et al)[34]	2017	5%	Reduction in compressive strength was higher for fly ash mineral filler than silica fume which was mainly due to the slower pozzolanic reaction of fly ash. Replacing fly ash with silica as a mineral filler was successful in mitigating loss in compressive strength for up to 20%CR.
	(P. N. Ojha et al.)[37]	2022	60%	Fly ash increase compressive strength, tensile strength, modulus of elasticity, porosity and water Absorption.
	(S.S.Rahman et all)[38]	2021	15%	Fly ash increase compressive strength35%, fly ash increase flexural strength43%.
	(S.K. Rao et all)[39]	2016	10%	The compressive strength, the UPV and the Dynamic modulus of elasticity were decreased with increase in fly ash content.
	(A. Kumar et all)[30]	2021	10%	The compressive strength of mixtures increases by 7% and The tensile strength of mixtures increases by 9%. The water absorption of RCC was calculated by 1.4%.
limestone	(S. I. Sarsam)[21]	2021	10%	The flexural strength increases by (96.2, 84, and 17.2) % and (109, 86, and 9.3) % for replacement of (10, 12, and 15) % of cement
	(S. I. Sarsam et all)[40]	2013	5%	The rate of increase in compressive strength is 109% for dense mixes and 115.8% for gap mixes. Increase 62% at mixes with 5% lime, increase in splitting tensile strength 150%.
	(S. N. SAOUDI et all)[41]	2022	0-10-15%	reduction in compressive strength of about 20%, tensile strength slightly decreases about 7%
	(Z. Huang et al.)[42]	2021	10%	increase compressive strength by 16% and decrease water absorption 18% , increase freezing and thawing resistance
M-sand	(S.K. Rao et all)[39]	2016	50%	The compressive strength, the UPV and the Dynamic modulus of elasticity were decreased with increase in fly ash content.
rice husk ash (RHA)	(E. K. Vahidi et all)[43]	2017	5%	Increase in compressive strength of about 15%, permeability decreases.
	(A.Dhanalakshmi et all) [44]	2023	20%	Increase in compressive strength of about 5%, increase in flexural strength of about 4.8%, increase in tensile strength of about 60%.
	(J. A. Del Carpio et al.)[45]	2011	5%	increase in compressive strength of about 50%
	(P. Chindapasirt a et all) [46]	2007	20%	increase in compressive strength of about 7%

steel filing	(A. A. Al-Shadeedi)[36]	2008	15%	steel filing increase in compressive strength of about 24%, increase flexural strength, increase tensile strength
Bagasse Ash	(A.Dhanalakshmi et al)[44]	2023	10%	Increase in compressive strength of about 5%, increase in flexural strength of about 4.8%, increase in tensile strength of about 60%.
Coal waste powder	(A.Modarres)[47]	2016	5%	increase in compressive strength of about 7%
Saudi Natural pozzolan (N.P)	(A. I. H. Malkawi) [27].	2017	10%	Natural pozzolan increase in compressive strength of about 15%.
Jordanian Natural pozzolan (N.P.)	(A. I. H. Malkawi) [27].	2017	10%	Natural pozzolan increase in compressive strength of about 7%.
Basalt rock flour.	(A.I. H. Malkawi)[27]	2017	10%	Increase in compressive strength of about 25%.
ground-granulated blast-furnace slag (GGBS)	(S. Moradi ,S. Shahnoori) [31]	2021	15%	The rate of increase in compressive strength is 3%, permeability decreases, decreasing the water absorption
	(M.ÖZTÜRK)[48]	2022	15%	Increase compressive strength, flexural strength, tensile strength (43%, 3%, 9%) respectively.
	(S. Saluja et al.)[49]	2019	40%	increase in compressive strength is 8.5%, increase in flexural strength is 5.4%, increase in split tensile strength is 26.6%, Optimum water content of RCC mixture decreases
	(Z. M. Abeda)[22]	2023	25%	increase in compressive strength is 10%, increase bulk density
	(S. K. RAO)[50]	2015	40%	increase in flexural strength of about 14%
POFA (Palm-oil-fuel-ash)	(V. Afroughsabet et al.)[51]	2023	80%	Achieved a compressive strength.
	(A. M. Ashteyat)[32]	2022	10%	decrease Compression Strength , Splitting strength , Flexural strength and Modulus of elasticity
	(J.N. Panchal)[52]	2021	10%	increase in compressive strength of about 2%, increase in flexural strength of about 2%, increase in tensile strength of about 1%,
Sugarcane ash	(S. Debbarma)[53]	2020	10%	reduce compressive, flexural and tensile strength
	(A.Choubdar)[54]	2021	10%	Reduce compressive, flexural and tensile strength.
	(M. Hemalatha et al.)[55]	2022	2.25%	The rate of increase in compressive strength is 11%
nano silica	(M.Adamu et al.)[56]	2018	1%	Increase fatigue and flexural strength.
	(v. Gokulanadh et al.)[57]	2022	2%	The rate of increase in compressive strength is 9% in room temperature, The rate of increase in compressive strength is 9% in 50c temperature, The rate of increase in compressive strength is 7% in 100c temperature,

5. CONCLUSIONS

The present information is an attempt has been made to enhance the properties of RCC mixes containing supplementary cementitious material (SCMs) based on a number of laboratory tests to obtain the optimum dosages of each mineral admixtures, according to the literature reviews mentioned above, the various admixtures utilized in concrete are as follows:

❖ Regarding the mechanical properties of RCC, attention has been paid to the compressive, and with the increase of the compressive strength, the flexural and splitting tensile strength has also improved. For better review, two mechanical properties are mentioned in table 3. Therefore, we can use the strengths mentioned in the table to improve the mechanical properties.

❖ Each mineral additive is partially replaced with cement in varying amounts. If the

percentage limit is exceeded, it has an influence on the strength properties of concrete, such as compressive, split, and flexural strength, as well as the durability properties.

❖ According to the above literature evaluations, the optimum amount of silica fume and RHA ranges from 5 to 15%.

❖ Typically, silica fume and metakaolin are used, increases hydration heat, and while others reduce it.RCC with metakaolin efficiently improves the strength properties. As the percentage of metakaolin increases, it also improves workability. Also RCC with fly ash improves the properties of the concrete and makes it more resistant to chemical attack.

❖ The addition of GGBS to cement increases the tensile and flexural strength of the RCC concrete. When GGBS is partially replaced in cement, fine aggregate is also partially replaced by other materials, which improves the

mechanical properties of the concrete. By using the mineral admixture in an acceptable percentage, all mineral admixtures reduce the bleeding in roller compacted concrete.

❖ Most of the time, it is preferable to use mineral admixtures that have more specific areas and smaller sizes to create highly dense and impermeable concrete.

❖ Also using different mineral admixtures in RCC have advantages and most of minerals could be using which are environment issue, as a results of the data analysis many parameters influence the improvement of the properties of RCC concrete by minerals, such as fineness, specific area ,sources of mineral admixture as well as percentage of used in the manufactured.

❖ The findings of the current study should also help with the application of SCMs for more durable RCC construction. Especially in road construction, also improve aesthetics of the road.

REFERENCE

Faqe, H (2020). Effect of Chemical Activators on the Compressive Strength of Cement-Slag Mortar. In Materials Science and Engineering Conference Series (Vol. 978, No. 1, p. 012004).

Mobina Taslimi Paein Afrakoti, Asskar Janalizadeh Choobbasti, Moein Ghadakpour, Saman Soleimani Kutanaei,(2020).Investigation of the effect of the coal wastes on the mechanical properties of the cement-treated sandy soil, Construction and Building Materials,Volume 239, 117848,ISSN 0950-0618,https://doi.org/10.1016/j.conbuildmat.2019.117848.

Singh G, Bansal RS (2017) Effect of partial replacement of cement by silica fume and sand by quarry dust on strength and durability of concrete. Int Res J Eng Techno 4(9):414–418.

Piti Sukontasukkul, Udomvit Chaisakulkiet, Pitthaya Jamsawang, Suksun Horpibulsuk, Chai Jaturapitakkul, Prinya Chindapasirt,(2019).Case investigation on application of steel fibers in roller compacted concrete pavement in Thailand, Case Studies in Construction Materials, Volume 11,2019, e00271,ISSN 2214-5095,https://doi.org/10.1016/j.cscm..e00271.

Audrius V., Rafal M., Ovidijus Š. (2021) ROLLER COMPACTED CONCRETE – BEST PRACTICE OF LITHUANIA, IOP Conf. Ser.: Mater. Sci. Eng. 1202 012010 DOI 10.1088/1757-899X/1202/1/012010

Chhorn, C., Hong, S. J., & Lee, S.-W. (2017). A study on performance of roller-compacted concrete for pavement. Construction and Building Materials, 153, 535–543. https://doi.org/10.1016/j.conbuildmat.2017.07.135.

ACI 207.5R, (2004). Roller compacted mass concrete Acids Man. Concr. Pract. p. 47.

A. Aghaeipour, M. Madhkhan, (2020). Mechanical properties and durability of roller compacted concrete pavement (RCCP)—a review, Road Mater. Pavement Des. 21https://doi.org/10.1080/14680629.2019.1579754.

ABU-BAKR, M., & MAHMOOD, H. F. (2022). INFLUENCE OF USING DIFFERENT TYPES OF FIBERS ON THE MECHANICAL PROPERTIES OF ROLLER COMPACTED CONCRETE A REVIEW. Journal of Duhok University, 25(2), 458-472. https://doi.org/10.26682/sjuod.2022.25.2.42

Shivani Shukla, Shalinee Shukla, Ayush Mittal, Tanu Singh, A review on use of coir fiber in road construction,Materials Today: Proceedings, Volume 65, Part 2,2022,Pages 1839-1845,ISSN 2214-7853,https://doi.org/10.1016/j.matpr.2022.05.017.

Mohamad ME, Mahmood AA, Min AYY, Nur Nadhira AR (2018) Palm oil fuel ash (POFA) and eggshell powder (esp) as partial replacement for cement in concrete. In: E3S web of conferences, 34, 01004

Toutanji HA, El-Korchi T (1995). The influence of silica fume on the compressive strength of cement paste and mortar. Cem Concr Res 25(7):1591–1602

Naveena SVD, Jagarapu DCK (2019) Experimental investigation on fiber reinforced beam column joint by partial replacement of cement with GGBS. Int J Recent Technol Eng 7(6):215–

- 219.
- Dubey S, Chandak R, Yadav RK (2015) Experimental study of concrete with metakaolin as partial replacement of OPC. *Int J AdvEng Res Sci* 2(6):38–40.
- Suleman Ahamed V, Siddiraju S (2016) Study of strength of concrete with palm oil fuel ash as cement replacement. *Int J Civil Eng Technol* 7(3):337–341.
- Masood Abu-Bakr, Hersh F. Mahmood, Azad A. Mohammed, (2022). Investigation of metakaolin and steel fiber addition on some mechanical and durability properties of roller compacted concrete, *Case Studies in Construction Materials*, Volume 16, 2022, e01136, ISSN 2214-5095, <https://doi.org/10.1016/j.cscm.2022.e01136>.
- Musa Adamu, Bashar S Mohammed and Nasir Shafiq (2017), effect of Mineral Filler type on Strength of Roller Compacted Rubber Crete for Pavement Applications, *IOP Conf. Ser.: Mater. Sci. Eng.* 201 012011, DOI 10.1088/1757-899X/201/1/012011.
- Adamu, Musa & Mohammed, Bashar & Shafiq, Nasir. (2017). Mechanical performance of roller compacted rubber Crete with different mineral filler. *Journal Teknologi.* 79. 10.11113/jt.v79.10200.
- Vahid Afroughsabet and Abir Al-Tabbaa, (2023). Effect of SAPs and polypropylene fibers on the freeze-thaw resistance of low carbon roller compacted concrete pavement, *MATEC Web of Conferences* 378, 08006, <https://doi.org/10.1051/mateconf/202337808006>
- Joe Arnaldo Villena Del Carpio, Glicério Trichês, and L.R. Prudêncio Jr,(). Replacing the Aggregate by Rice Husk Ash in Roller Compacted Concrete for Composite Pavements, *Pavements and Materials: Recent Advances in Design, Testing and Construction* [https://doi.org/10.1061/47623\(402\)3](https://doi.org/10.1061/47623(402)3).
- Jai Narendra Panchal, S.P. Challagulla and I. Siva Kishore, (2021). Influence of Palm Oil Fuel Ash on Strength Properties of Concrete, *IOP Conf. Ser.: Mater. Sci. Eng.* 1197 012082, DOI 10.1088/1757-899X/1197/1/012082
- Saad Issa Sarsam (2021). Influence of Additives on Flexural Strength of Roller Compacted Concrete, *Journal of Cement Based Composites* 1 (2021) 1-6, <https://doi.org/10.36937/cebacom.2021.001.001>
- Ziyad M. Abed, Hisham K. Ahmedb, Wasan I. Khalila, (2023). Optimization of Silica Fume and Slag in Roller Compacted Concrete by Taguchi Method, *Engineering and Technology Journal* 41 (05) 724 -733
- Naraindas Bheel , Paul Awoyera , Irfan Ali Shar, Samiullah Sohu, Suhail Ahmed Abbasi, and A. Krishna Prakash, (2021). Mechanical Properties of Concrete Incorporating Rice Husk Ash and Wheat Straw Ash as Ternary Cementitious Material, *Advances in Civil Engineering*, Article ID 2977428, 13 pages <https://doi.org/10.1155/2021/2977428>
- Mohammad Momeen U, Islam, U. Johnson Alengaram, Mohd Zamin Jumaat, (2021). Fresh and Hardened Properties of palm oil fuel ash (POFA) based lightweight concrete from palm oil industrial wastes, *Proceedings of International Conference on Planning, Architecture & Civil Engineering*, Rajshahi University of Engineering & Technology .
- Ebrahim Khalilzadeh Vahidi, Maryam Mokhtari Malekabadi, Abbas Rezaei, Mohammad Mahdi Roshani, and Gholam Hossein Roshani, (2017). Modeling of mechanical properties of roller compacted concrete containing RHA using ANFIS. *Computers and Concrete*, Vol. 19, No. 4 (2017) 435-442 DOI: <https://doi.org/10.12989/cac.2017.19.4.435>.
- Gai Fei Peng, Juan Yang, (2016). Influence of Rice Husk Ash on the properties of Concrete: a Review, *International Forum on Energy, Environment and Sustainable Development (IFEESD)*, DOI 10.2991/ifeesd-16.2016.25.
- Abdallah I. Husein Malkawi, Ehab Shatnawi , and Dima A. Husein Malkawi ,(2017). A comparative study of physical and chemical

- properties of different pozzolanic materials used for roller compacted concrete RCC dams, MATEC Web of Conferences 120, 02025, DOI: 10.1051/mateconf/20171200
- Abed, Z., Ahmed, H., & Khalil, W. (2023). Optimization of Silica Fume and Slag in Roller Compacted Concrete by Taguchi Method. *Engineering and Technology Journal*, 41(5), 724-733. Doi: 10.30684/etj.2023.138600.1411
- M. Hemalatha, Veerendrakumar C. Khed, G. Sri Harsha, and Musa Adamu,(2022) Feasibility study on compressive strength of roller compacted concrete pavement using nano silica and natural fiber AIP Conference Proceedings 2426, 020006 <https://doi.org/10.1063/5.0127345>
- Aneel Kumar, Naraindas Bheel, Israr Ahmed, Samar Hussain Rizvi, Rabinder Kumar, and Ashfaque Ahmed Jhatial,(2022).. Effect of silica fume and fly ash as cementitious material on hardened properties and embodied carbon of roller compacted concrete. *Environ Sci Pollut Res* 29, 1210–1222, <https://doi.org/10.1007/s11356-021-15734-0>.
- Saeed Moradi, Shore Shahnoori, (2021). Eco-friendly mix for Roller-Compacted Concrete: Effects of Persian-Gulf-Dredged marine sand on durability and resistance parameters of concrete, *Construction and Building Materials*, Volume 281, 122555, ISSN 0950-0618, <https://doi.org/10.1016/j.conbuildmat.2021.122555>.
- Ashteyat, A. M., Al Rjoub, Y. S., Obaidat, A. T., Kirgiz, M., Abdel-Jaber, M. A., & Smadi, A. (2022). Roller compacted concrete with oil shale ash as a replacement of cement: Mechanical and durability behavior. *International Journal of Pavement Research and Technology*, 1-18.
- Chennakesava, C., Kashyap, A. M. N., Lavakumar, S. K. V. S. T., & Sasikala, G. Flexural Strength of Roller Compacted Concrete using Mineral Admixtures.
- Adamu, M., Mohammed, B. S., & Shafiq, N. (2017, May). Effect of mineral filler type on strength of roller compacted rubbercrete for pavement applications. In *IOP conference series: materials science and engineering* (Vol. 201, No. 1, p. 012011). IOP Publishing.
- Xupeng, C., Zhuowen, S., & Jianyong, P. (2021). Effects of active mineral admixture on mechanical properties and durability of concrete. *Materials Research Express*, 8(11), 115506.
- Hamzah, A. A., & Al-Shadeedi, M. B. (2008). Evaluation of properties of roller compacted concrete. *Al-Nahrain Journal for Engineering Sciences*, 11(3), 366-373.
- Ojhaa, P. N., Singh, B., Prakashc, S., Singhd, P., Mandree, M. K., & Kumarf, S. (2022). Effect of high ratio fly ash on roller compacted concrete for dam construction.
- Rahman, S. S., & Khattak, M. J. (2021). Roller compacted geopolymer concrete using recycled concrete aggregate. *Construction and Building Materials*, 283, 122624.
- Rao, S. K., Sravana, P., & Rao, T. C. (2016). Experimental studies in Ultrasonic Pulse Velocity of roller compacted concrete pavement containing fly ash and M-sand. *International Journal of Pavement Research and Technology*, 9(4), 289-301.
- Sarsam, S. I., Salih, A. A., & Abdullah, S. G. (2013). Effect of hydrated lime on the properties of roller compacted concrete. *Journal of Engineering*, 19(3), 377-387.
- Saoudi, N., Cherfa, H., Saoudi, B., & Zaanoun, B. (2022). The Compaction of Energy and Properties of Roller-Compacted Concrete Pavement with Fillers. *Slovak Journal of Civil Engineering*, 30(4), 23-30.
- Huang, Z., Sookree, E. W., Mohamoud, A. H., & Wang, Z. (2021). Influence of Limestone Powder and Fly Ash on the Freezing and Thawing Resistance of Roller-Compacted Concrete. *KSCE Journal of Civil Engineering*, 25, 2501-2507.
- Vahidi, E. K., Malekabadi, M. M., Rezaei, A., Roshani, M. M., & Roshani, G. H. (2017). Modelling of mechanical properties of roller compacted concrete containing RHA using

- ANFIS. *Computers and Concrete*, 19(4), 435-442.
- Dhanalakshmi, A., Jeyaseela, J., Karthika, S., & Margret, A. L. (2023). An Experimental Study on Concrete with Partial Replacement of Cement By Rice Husk Ash and Bagasse Ash. In *E3S Web of Conferences* (Vol. 387, p. 03004). EDP Sciences.
- Villena, J., Trichês, G., & Prudêncio, Jr, L. R. (2011). Replacing the aggregate by rice husk ash in roller compacted concrete for composite pavements. In *Pavements and materials: recent advances in design, testing and construction* (pp. 19-27).
- Chindaprasirt, P., Kanchanda, P., Sathonsaowaphak, A., & Cao, H. T. (2007). Sulfate resistance of blended cements containing fly ash and rice husk ash. *Construction and Building Materials*, 21(6), 1356-1361.
- Modarres, A., Hesami, S., Soltaninejad, M., & Madani, H. (2018). Application of coal waste in sustainable roller compacted concrete pavement-environmental and technical assessment. *International Journal of Pavement Engineering*, 19(8), 748-761.
- ÖZTÜRK, M. (2022). Elevated Temperature Resistance of Mortars Including Ground Granulated Blast Furnace Slag, Fly ash and Silica Fume. *Osmaniye Korkut Ata Üniversitesi Fen Bilimleri Enstitüsü Dergisi*, 5(1), 143-153.
- Saluja, S., Goyal, S., & Bhattacharjee, B. (2019). Strength properties of roller compacted concrete containing GGBS as partial replacement of cement. *Journal of Engineering Research*, 7(1).
- Rao, S. K., Sravana, P., & Rao, T. C. (2015). Investigation on pozzolanic effect of mineral admixtures in roller compacted concrete pavement. *I-manager's Journal on Structural Engineering*, 4(2), 28.
- Afroughsabet, V., & Al-Tabbaa, A. Effect of SAPs and polypropylene fibres on the freeze-thaw resistance of low carbon roller compacted concrete pavement. In *MATEC Web of Conferences* (Vol. 378, p. 08006). EDP Sciences.
- Panchal, J. N., Challagulla, S. P., & Kishore, I. S. (2021, November). Influence of palm oil fuel ash on strength properties of concrete. In *IOP Conference Series: Materials Science and Engineering* (Vol. 1197, No. 1, p. 012082). IOP Publishing.
- Debbarma, S., Ransinchung, G. D., Singh, S., & Sahdeo, S. K. (2020). Utilization of industrial and agricultural wastes for productions of sustainable roller compacted concrete pavement mixes containing reclaimed asphalt pavement aggregates. *Resources, Conservation and Recycling*, 152, 104504.
- Choubdar, A., Farajollahi, A., & Ameli, A. (2021). Investigation of the Effect of the Utilization of Industrial and Agricultural Wastes for Productions of Sustainable Roller Compacted Concrete Pavement Mixes Containing Reclaimed Asphalt Pavement Aggregates. *Journal of Transportation Research*, 18(2), 14-1.
- Hemalatha, M., Khed, V. C., Harsha, G., & Adamu, M. (2022, December). Feasibility study on compressive strength of roller compacted concrete pavement using nano silica and natural fibre. In *AIP Conference Proceedings* (Vol. 2426, No. 1). AIP Publishing.
- Adamu, M., Mohammed, B. S., Shafiq, N., & Shahir Liew, M. (2018). Effect of crumb rubber and nano silica on the fatigue performance of roller compacted concrete pavement. *Cogent engineering*, 5(1), 1436027.
- Gokulanadh, V., Khed, V. C., & Adamu, M. (2022, December). Feasibility study on temperature tests of roller compacted concrete pavement using nano silica and banana fiber. In *AIP Conference Proceedings* (Vol. 2426, No. 1). AIP Publishing.